

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5 : A01N 59/26, C01B 25/10, 25/16 C01B 25/32, A61F 2/28	A1	(11) International Publication Number: WO 94/08458 (43) International Publication Date: 28 April 1994 (28.04.94)
(21) International Application Number: PCT/US93/09086 (22) International Filing Date: 24 September 1993 (24.09.93) (30) Priority data: 07/963,481 16 October 1992 (16.10.92) US (71) Applicant: NORIAN CORPORATION [US/US]; 1025 Terra Bella Avenue, Mountain View, CA 94043 (US). (72) Inventor: CONSTANTZ, Brent, R. ; 195 Northridge Drive, Los Gatos, CA 95066 (US). (74) Agents: ROWLAND, Bertram, I. et al.; Flehr, Hohbach, Test, Albritton & Herbert, 4 Embarcadero Center, Suite 3400, San Francisco, CA 94111-4187 (US).		(81) Designated States: European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: CARBONATED HYDROXYAPATITE COMPOSITIONS AND USES (57) Abstract Carbonated hydroxyapatite compositions and their preparation are described. The compositions are biologically resorbable and are prepared as flowable masses which can be administered by syringe to set <i>in situ</i> to serve as a support structure, filler, prosthesis or the like. Optionally the compositions may include proteins or serve as a depot for compositions of pharmacological interest.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TC	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

CARBONATED HYDROXYAPATITE COMPOSITIONS AND USES**CROSS-REFERENCE TO RELATED APPLICATIONS**

This application is a continuation-in-part of application Serial No. (A55116-8) filed July 23, 1992, which is a continuation-in-part of application Serial No. 5 07/722,880 filed June 28, 1991, which is a continuation-in-part of application Serial No. 650,462, filed February 4, 1991, which is a continuation-in-part of application Serial No. 393,579, filed August 14, 1989, which is a continuation of application Serial No. 358,716, which is a 10 continuation of application Serial No. 183,770, filed April 28, 1988, now U.S. Patent No. 4,880,610, whose disclosures are incorporated herein by reference.

INTRODUCTION**15 Technical Field**

The field concerns the preparation of substantially pure compositions of carbonate-substituted forms of hydroxyapatite, and the biomedical use of such compositions.

20

Background

A number of calcium phosphate minerals, such as hydroxyapatite, fluorapatite, octacalcium phosphate, whitlockite, brushite and monetite may have application as 25 biocompatible materials. The various crystalline forms of the calcium phosphate minerals can confer different

- 2 -

physical properties that may be more or less desirable for a specific biomedical application. For instance, octacalcium phosphate and whitlockite are less resorbable than brushite or monetite (Brown and Chow, Ann. Rev. of Materials Science (1976) 6:213-236).

Of particular interest are the apatites. Apatite is a general term for a wide range of compounds represented by the general formula $M^{2+}_{10}(ZO_4^3)_6Y_2$, where M is a metal atom, particularly an alkali or alkaline earth atom, ZO_4 is an acid radical, where Z may be phosphorous, arsenic, vanadium, sulphur, silicon, or may be substituted in whole or in part by carbonate (CO_3^{2-}), and Y is an anion, usually halide, hydroxy, or carbonate. When ZO_4^3 is partially or wholly replaced by trivalent anions (such as CO_3^{2-}) and/or Y is partially or wholly replaced by divalent anions, then charge balance may be maintained in the overall structure by additional monovalent cations (such as Na^+) and/or protonated acid radicals (such as HPO_4^{2-}).

Hydroxyapatite (HAp), as well as its various forms, has been the focus of substantial interest because it is a major structural component of biological tissues such as bone, teeth, and some invertebrate skeletons. There are many situations where bone has been broken, surgically removed, destroyed, degraded, become too brittle, or been subject to other deteriorating effects. In many of these situations it would be desirable to be able to replace the bone structure or strengthen the bone structure. In providing materials to substitute for natural bone, teeth, or other calcified tissues, there are a number of restraints on the natural composition of the material.

Dental applications might prefer a fluoride substituted hydroxyapatite, i.e. francolite, that would reduce solubility and increase resistance to decay.

The material should ideally possess certain characteristics that facilitate the production, storage life, and biomedical application of the material. Specifically, a material which could be a material which could be fingerpacked in an open surgical procedure or

- 3 -

percutaneously injected as a flowable composition to fill voids or completely fill-in areas deficient of hard bone is very desirable. Where the material is to be placed in the body and formed and hardened in situ, a variety of considerations come to the fore. For example, the rate at which hydroxyapatite forms as well as the extent to which the formation of hydroxyapatite is exothermic or may generate gas can also be important. Where the reaction is highly exothermic, it may cause thermal necrosis of the surrounding tissue.

As the final form of the material must be stable under physiological conditions, so must the form in which the material is introduced be stable while it is hardening in the environment to which it is introduced, as must be any intermediate products of the formation reaction.

The material should also be physiologically acceptable at all phases of curing to the final product, so as to avoid the initiation of clotting, inflammatory responses, and the like. Two different forms of apatite are particularly desirable: One being an hydroxyapatite or a fluoridated derivative thereof that is non-resorbable in vivo; the other includes forms of apatite that are substantially resorbable in vivo. In addition, both forms of apatite must usually be strong and non-friable. Furthermore, there should be a strong adhesion between the material and the remaining bone or calcified tissue. Also, the material should desirably be able to substitute some of the other functions of natural bone such as: accommodating stem cells; allowing infiltration by cells normally resident in natural bone such as osteoclasts, osteoblasts, and the like; allowing remodeling of the material by the infiltrating cells followed by new bone in-growth; and acting in metabolic calcium exchange in a manner similar to native bone.

Carbonate has been shown to inhibit crystal growth of HAP (Blumenthal, et al., Calcif. Tissue Int. (1984) 36:439-441; LeGeros, et al., "Phosphate Minerals in human tissues", in Phosphate Minerals (Berlin), J. Nriagu (eds):

- Springer, 1984, pp. 351-385; LeGeros, et al., J. Dent. Res. (1989) 68:1003; Nauman and Neuman, *The Chemical Dynamics of Bone Mineral*, University of Chicago Press, Chicago, (1958); Newesley, Arch. Oral Biol. (1961) 6:174-180; Posner, Clin. Orthop. (1985) 200:87-99).
- Carbonates are present in the apatites of hard tissues, and their presence alters the properties of stoichiometric apatite. Carbonate has been described as causing: 1) a reduction in crystallite size, 2) changes in the morphologies of the mineral phase from needles and rods to equi-axis crystals (spheroids), 3) contraction of the a-axis, as well as an expansion in the c-axis, 4) internal strain, and 5) chemical instability (LeGeros, et al., supra, 1984; LeGeros, et al., supra, 1989). All of these factors lead to higher solubilities of carbonate-substituted HAp. The x-ray diffraction patterns as well as the radial distribution function are changed considerably in that as the concentration of carbonate increases, the patterns become more amorphous in character (LeGeros et al., supra 1989; Glimcher, M.J., "Recent studies of the mineral phase in bone and its possible linkage to the organic matrix by protein-bound phosphate bonds", *Phil. Trans. R. Soc. London Ser. B.*, 304, 479-508). The line broadening observed in the diffraction pattern is caused by decreasing crystallite size and crystallinity. In addition to inhibiting HAp crystal growth, carbonate substitution markedly increases the solubility of HAp (Nelson, et al., Ultramicroscopy (1986) 19:253-266. Another interesting experimental finding was that, whether the carbonates are structurally bound within, or absorbed onto HAp, differences in dissolution behavior were observed. This suggests that dissolution increased in HAp's containing structurally bound carbonates, while decreasing in HAp's with absorbed CO_3^{2-} .
- The decrease in dissolution was explained by the fact that hydronium ions had to compete for the surface of HAp, hence the deposition of the CO_3^{2-} layer was required.

- 5 -

- The extent of carbonate uptake during HAP precipitation under normal physiological conditions is approximately 1% by weight CO_3^{2-} (Posner, supra, 1985). Bone consists of approximately 4% by weight CO_3^{2-} . Thus,
- 5 HAP precipitation reactions in air generally contain relatively low concentrations of carbonate. Bone mineral apatite with a level of carbonate between 2% and 10% by weight has been referred to by convention as dahllite (McConnell, J. Dent. Res. (1952) 31:53-63 and McConnell,
- 10 Clin. Orthopaed. (1962) 23:253-268).
- Carbonates can substitute in both the Z and Y sites of the apatite structure, and it is generally accepted that carbonates substitute for PO_4^{3-} groups during precipitation reactions leading to HAP formation. More
- 15 specifically, HAP products formed at lower temperature exhibit carbonate substitution at the phosphate sites, and due to its smaller size, a decrease in the a-axis of the apatite results (LeGeros, et al., supra, 1984 and LeGeros, et al., supra, 1989). Conversely, in most high
- 20 temperature apatites, the carbonates are found in the vicinity of the six fold axis, where they replace hydroxyl ions. Since the carbonate is larger than the hydroxyl ion, an increase in the a-axis results (Brown and Chow, (1986), supra).
- 25 The skeleton is the reservoir for almost all of the body's calcium and most of its phosphorus and magnesium (Avioli and Krane, Metabolic Bone Disease and Clinically Related Disorders, 2nd Ed., 1990, W.B. Saunders Co., Philadelphia, p. 2). The carbonate levels in human enamel
- 30 have been shown to increase in concentration from the surface to the dentin. The carbonate concentration in the surface enamel has also been shown to decrease with age (Brudevold and Soremark, Chemistry of the mineral phase of enamel, Miles (ed.), In: Structural and Chemical
- 35 Organizations of Teeth. Academic Press, New York, 1967, Vol. II, p. 247. The ease of ionic substitution in the lattice of apatite allows for the ionic substitution of ions from the fluids surrounding the bone, and vice versa.

- 6 -

This implies that hard tissues act as a regulatory reservoir for certain ions by incorporating ions into its structure when ionic concentration in the serum rises too high, and dissolving ions when the body is deficient in them. Possible candidates for this form of regulation might include some of the inorganic constituents of serum such as ionized and complexed calcium, inorganic phosphates, magnesium, bicarbonate, sodium, chloride, potassium, among others (Eidleman, et al., Calcif. Tissue Int. (1987a) 41:18-26; Eidelman, et al., Calcif. Tissue Int. (1987b) 40:71-78; Meyer and Fleisch, Miner. Electrolyte Metab. (1984) 10:249-258).

Carbonate is especially important in hard tissue in that it appears to be required for the cellular infiltration of bone by osteoclasts, osteoblasts and other bone resident cells. Since osteoclasts, osteoblasts and the like are involved in mineral replacement and bone remodeling, any synthetic apatite-associated bioimplant would preferably use a carbonated form of apatite, or dahllite. Because dahllite can be remodeled by the bodies natural processes, the dahllite component of an implant should, through the action of osteoclasts and osteoblasts, eventually be replaced by natural bone. Thus, dahllite implants should eventually gain many or all of the desirable features of natural bone such as increased strength, elasticity and durability.

— Previous methods of chemically forming monolithic bodies of hydroxyapatite have not produced dahllite or hydroxyapatites with physiologically significant levels of structurally incorporated carbonate. This is primarily because the acid present in the reactions of other methods tend to react with the carbonate to produce gaseous CO₂. Gaseous escape removes carbonate from the reaction which is forming apatite and can result in a product that is substantially more friable than that generally desired by virtue of the trapped gas bubbles disrupting the structural integrity of the product. Thus, a major obstacle to the production of dahllite has been devising a

- 7 -

method to maintain carbonate in the product despite the presence of the acid required to form the apatitic structure.

5 Relevant Literature

- Patents of interest include U.S. Patent Nos. 3,787,900; 3,913,229; 3,679,360; 4,097,935; 4,481,175; 4,503,157; 4,612,053; 4,659,617; and 4,693,986. See also, Arends and Jongebloed, Rec. Trav. Chim. Pays-Bas (1981) 100:3-9. Use of calcium phosphate as a sealer-filler material is described in Chohayeb et al., J. Endodontics (1987) 13:384-387 and Lowenstam and Weiner, On Biomineralization, (1989), Oxford University Press, New York. See also, Ohwaki et al., 13th Ann. Mtg. of the Soc. for Biomaterials, June 2-6, 1987, New York, NY, p209.

SUMMARY OF THE INVENTION

- Compositions comprised of dahllite, analogs thereof, or otherwise carbonate-substituted forms of hydroxyapatite (dahllite-like compositions) are provided that are useful in a variety of biomedical applications. The compositions can be prepared such that they are flowable, moldable, and capable of hardening in situ. The compositions harden into monolithic polycrystalline structures that can be shaped subsequent to hardening.

DESCRIPTION OF THE SPECIFIC EMBODIMENTS

- Compositions are provided that are comprised of substantially pure (greater than 80% by weight) dahllite-like compositions referred to as carbonated hydroxyapatite that can be produced substantially free of the blood-borne or organic components of natural bone. The compositions can be used to substitute many of the functions of naturally occurring calcified tissues or in the repair of such tissues, in particular teeth and bone. The dahllite or franc lite-like products can be readily formed by combining the wet and dry reactants to provide a substantially uniform mixture, shaping the mixture as

- 8 -

appropriate, and allowing the mixture to harden. During hardening, the mixture crystallizes into a solid and essentially monolithic apatitic structure. The dahllite and francolite-like apatitic compositions can also be
5 shaped subsequent to hardening. Alternatively, the dahllite or francolite-like apatitic compositions can be precursor reaction mixtures placed into an appropriate section of the body and hardened and/or shaped in situ.

The composition of the carbonated hydroxyapatite may
10 vary, frequently being non-stoichiometric in having incorporated extra hydrogen atoms. Also, the calcium/phosphate ratio may vary, where the ratio may be as low as 1.33 (1.67 is the natural ratio), so that there is a defective lattice structure from the calcium
15 vacancies and as high as 2.0. For a ratio of 1.33, there will be two calcium ions absent. The extra hydrogens may be up to about 2 hydrogen ions per phosphate, usually not more than about one hydrogen ion per phosphate. The ions will be uniformly distributed throughout the product and
20 for the most part, the composition will be monophasic having a single crystal structure. As compared to sintered hydroxyapatite and hydrothermally prepared hydroxyapatite, the X-ray diffraction and Fourier transform infra-red spectra of the subject compositions
25 are substantially different.

The reactants will generally consist of a phosphoric acid source substantially free of unbound water, an alkali earth metal, particularly calcium, source, optionally crystalline nuclei, particularly hydroxyapatite or calcium
30 phosphate crystals, calcium carbonate, and a physiologically acceptable lubricant, such as water, which may have various solutes. The dry ingredients may be pre-prepared as a mixture and subsequently combined with the liquid ingredients under conditions where
35 substantially uniform mixing occurs. Where gases are evolved the mixture is agitated to cause the release of large pockets of gas.

- 9 -

The phosphoric acid source may be any partially neutralized phosphoric acid, particularly up to and including complete neutralization of the first proton as in calcium phosphate monobasic. Alternatively or
5 additionally, it can consist of orthophosphoric acid, possibly in a crystalline form, that is substantially free of combined water. The acid source will generally be about 15 to 35 weight percent of the dry components of the mixture, more usually 15 to 25 weight percent.

10 In selecting the calcium source, particularly where the calcium source serves a dual role of providing calcium and acts in a neutralizing capacity, one must consider that the desired final product will depend on the relative ratios of calcium and phosphate. Calcium sources will
15 generally include counterions such as carbonate, phosphate or the like. Of particular interest are dual sources of calcium phosphate and phosphate such as tetracalcium phosphate (C_4P) or tricalcium phosphate (C_3P). Tetracalcium phosphate or tricalcium phosphate may
20 typically be present in the mixture at from about 0 to 70 weight percent, more usually from about 0 to 40 weight percent, and preferably from about 2 to 18 weight percent of dry weight of the dry components of the mixture. With calcium carbonate present to neutralize the acid and to
25 serve as a source of calcium and carbonate, the reaction will result in relatively little temperature rise; however, there is substantial evolution of gas which must be released during mixing. Calcium carbonate will be present in the mixture from about 2 to 70 weight percent,
30 more usually from about 2 to 40 weight percent, and preferably from about 2 to 18 weight percent of dry weight of the dry components of the mixture. Calcium hydroxide may also be present in the mixture from about 0 to 40 wt.%, more usually from about 2 to 25 wt.%, and
35 optimally from about 2 to 20 wt.%.

Halides such as fluorine and chlorine may be added to form fluorapatite (francolite), or chlorapatite respectively. Various sources of fluoride or chloride may

- 10 -

be employed. Generally, the sources will include either soluble salts such as calcium chloride, calcium hexafluorosilicate or sodium fluoride or, less desirably, the source may be added as a dilute acid in the aqueous lubricant, generally at concentrations of less than about 1 M. Halides, if present at all, will constitute from about 0 to 4 weight percent, more usually from about 2 to 4 weight percent, preferably from about 3 to 4 weight percent of dry weight. Usually at least about 5, more usually at least about 10% of the hydroxyl groups will be replaced, and up to 100%. Francolite is of particular interest because of the potential dental applications of this partially fluorine substituted form of dahllite.

The various dry components may be combined prior to the addition of the wet components. Mixing will be used to combine the ingredients and can be used to regulate the extent of the inter-ingredient reactions. Any or all of the dry ingredients may be added prior to the initiation of mixing or prior to the completion of mechanical mixing. Methods of mixing can include ball milling, Brabender mixing, rolling between one or more rollers and a flexible container, or the like. Preferably, mixing will be thorough and will occur for a relatively short time or until a uniform dispersal of ingredients is obtained.

By varying the proportion of liquid lubricant, particularly water, added to the subject mixtures, the fluidity of the composition can be varied with respect to flowability and viscosity. Besides or in combination with water, other water miscible pharmacologically acceptable liquids may be used, particularly alkanols, more particularly polyols, such as ethylene glycol, propylene glycol or glycerol, usually being present in less than about 10 volume percent in an appropriate medium. The liquid will generally be from about 15 to 50, more usually from about 20 to 35 weight percent of the entire composition. Various solutes may be included in the aqueous medium. Of particular interest is the use of a gel or colloid, which has as a solute alkali metal

- 11 -

hydroxide, acetate, phosphate, or carbonate, particularly sodium, more particularly phosphate or carbonate, at a concentration in the range of about 0.01 to 2 M, particularly 0.05 to 0.5 M, and at a pH in the range of about 6-11, more usually about 7-9, particularly 7-7.5.

Implantation may be by syringe or catheter injection; particularly, the composition may be used as a paste that passes through a needle in the range of about 10-18 gauge, preferably about 14-16 gauge. Alternatively, if less lubricant is added, the composition is kneadable or moldable, being capable of forming clay-like putty that may be molded prior to setting. By varying the amount of lubricant employed, the setting time of the compositions can also be varied.

After mixing, the mixture is allowed to anneal while remaining quiescent, followed by an extended period of time during which the mixture hardens. During hardening, crystal growth occurs and the product becomes an integral mass. Hardening will take at least about 5 minutes, usually at least about 15 minutes, and not more than about 20 minutes. Compounds produced in this manner will have a wide variety of desirable properties for use in physiological applications.

The claimed compositions will contain, structurally incorporated into the apatitic structure, between about 2% and about 10% carbonate by weight, usually between 2.5% to 7%,—and optimally between about 4% to about 6% carbonate by weight.

The subject compositions are biocompatible having a pH in the range of about 5.5-8.5, usually in the range of about 6-7.5. They can be prepared so that they can be administered to an environment having a temperature in the range of about 0-45°C, usually 20-40°C, and optimally about normal physiological temperature, 37°C. The compositions have low or no toxicity when prepared in accordance with described methods, are substantially inactive as to detrimental interactions with various host components in vivo, and are readily implantible.

- 12 -

Furthermore, they are readily resorbable in vivo so as to be replaced by natural bone.

Various additional components may be included during the formation of the carbonated hydroxyapatite, dahllite.

- 5 Of particular interest are pharmacologically active agents, proteins, polysaccharides, or other biocompatible polymers, or the like. Of particular interest are proteins involved in skeletal structure such as different forms of collagen, especially Type I, fibrin, fibrinogen, 10 keratin, tubulin, elastin, and the like, or structural polysaccharides, such as chitin. Pharmacologically active agents might include drugs that enhance bone growth, serve as a variety of cell growth factors, or act as anti-inflammatory or anti-microbial agents. Examples of 15 such proteins might include but not be limited to: bone morphogenetic protein, cartilage induction factor, platelet derived growth factor, and skeletal growth factor. Pharmacologically active or structural proteins may be added as an aqueous dispersion or solution.
- 20 Usually the protein will be present in from about 1-10 wt % of the aqueous dispersion. The protein will be present in the final composition after setting in from about 0.01 to 10, usually from about 0.05 to 5 weight percent. The amount of water added to the compositions to 25 which protein in aqueous dispersion has also been added will be adjusted accordingly. By varying the proportions of the reactants, compositions with varying and predictable rates of resorption in vivo, can be made. Thus, the subject compositions enable one of ordinary 30 skill in the art to add drug and inorganic components both subsequent to and during, and possibly prior to, the formation of the subject compositions in order to practice an implantable or injectable time-release delivery platform for drugs, inorganic mineral supplements, or the 35 like.

When used as cements or fillers, the subject compositions bond to other apatites when applied to an apatitic surface, such as bones or teeth which are mainly

- 13 -

comprised of dahllite and collagen. The applicable compositions are able to strongly adhere and bond to surfaces that are wet or coated with saliva, blood or lymphatic fluid, will fill voids, and conform to irregular surfaces such as concavities and convexities. The compositions may be applied as a continuous mass without the formation of fragments or loose particles to a significant degree. Furthermore, the subject compositions are found to be structurally compatible in providing for the structural functions of replaced connective tissue.

The subject compositions can be used to form carbonated hydroxyapatite coatings on bioimplants or other formed objects.

The subject composition, as a flowable or formable product, can serve as a bone cement, or an infiltrate cement for the treatment of osteoporotic bone.

Paste or clay-like mixtures of product are provided that may be formed and hardened into a monolithic carbonated hydroxyapatite product, either externally or in situ.

Of particular interest is preparation of the subject carbonated hydroxyapatite by a process whereby a calcium source, at least one component of which is calcium carbonate, and an acidic phosphate source, optionally comprised of ortho phosphoric acid crystals substantially free of uncombined water, are mechanically mixed for sufficient time for a partial reaction of said calcium source and acidic phosphate source. The partially reacted composition can be subsequently mixed with a physiologically suitable lubricant which varies the fluidity of the product, allows the substantially complete reaction of the reactants, and eventually results in a monolithic solid carbonated hydroxyapatite product. The final mixture may be subsequently shaped and hardened, hardened then shaped, or placed in the body and hardened in situ. The carbonated hydroxyapatite of the subject process will have substantially reduced or non-exothermic setting which may better provide for the stability of

- 14 -

intr oduced pharmacological agents, and, when hardened
in situ, is desirable for purposes of patient comfort.
The compositions of this process are also applicable as
bone cements or fillers, dental or endodontic filling
5 agents, coatings for bioimplantible substrates, or formed
into suitable shapes before or after hardening into a
monolithic structure.

The calcium source used in the above process will
typically include a mixture of tetracalcium phosphate
10 (C_4P) and calcium carbonate (CC) with C_4P typically present
in from about 55 to 75 wt.%, or more usually 60-70 wt.%,
and CC typically present in from about 1 to 40 wt.%, or
more typically 2 to 18 wt.% of the dry weight of the total
reaction mixture.

15 The acid phosphate source will be about 15 to 35, or
more usually 15 to 25 wt.% of the dry weight of the
reaction mixture.

An alternative formula will typically include a
mixture of tricalcium phosphate (C_3P), calcium carbonate
20 (CC), and calcium hydroxide (CH) with C_3P typically
present in from about 50 to 90 wt.%, or more usually 75 to
90 wt.%, CC typically present from about 1 to 40 wt.% or
more usually 2 to 18 wt.%, and CH typically present from
about 0 to 40 wt.% or more usually 2 to 20 wt.% of the dry
25 weight of the total reaction mixture.

The acid phosphate source for this alternative
mixture will be about 5 to 35 wt.% or more usually 5 to
25 wt.% of the dry weight of the reaction mixture.

A fluoride source may generally be added to the
30 mixture and, if at all present, will be in an amount from
about 0 to 4 wt.%, preferably 3 to 4 wt.% of dry weight.

After the dry ingredients are combined, the
reactants will be placed in intimate contact by mechanical
mixing or milling. Prior to the completion of
35 mixing/milling, proteins and/or small organic molecules,
especially those containing pharmacological significance
as indicated earlier, may be added to the mixture to alter
the physical or physiological properties of the final

- 15 -

product. The amount of additive will generally vary from about 1 to 40 weight percent, more usually from about 1 to 25 weight percent of the inorganic materials. It may be preferred that the additive be combined with the inorganic materials before mixing/milling.

Mechanical mixing may be by any form that results in an intimate mixing of the reactants. A variety of equipment may be used for these purposes including ball mills, planetary mills, centrifugal mills, mechanofusion systems, air pulverizers, jet mills, vibratory mills, colloid mills, attrition mills, disc mills, and the like.

The course of mixing can be monitored by periodically removing samples and testing whether or not the samples result in the formation of a product with the desired properties after mixing with an aqueous medium and subsequent hardening.

During mixing or milling, the walls of the mixing vessel may be periodically scraped to better promote a more uniform product. The milling media should remain stable as inert throughout the process as would media such as alumina, zirconia, tungsten carbide, boron carbide, etc.

The product of the above process will have undergone a relatively stable partial reaction and will require less lubricant to provide a workable mixture as well as a reduced setting time.

— All of the above-mentioned products or their precursors may be sterilized by gamma-irradiation or other applicable methodologies prior to bioimplantation.

The following example is offered by way of illustration and not by way of limitation.

EXPERIMENTAL

Example 1

In a chilled mortar, 11.54 g of tetracalcium phosphate (TCP), 1.40 g of calcium carbonate, 2.06 g of ortho-phosphoric acid and 7.5 g of 0.1 M sodium phosphate were mixed with a chilled pestle (mixed bases for 15 sec.,

- 16 -

followed by 30 sec. of mixing of both acid and bases, then 3 min. of wet mixing of the combined solution, acids and bases). The completed mixes were injectable and free flowing and were immediately put into bovine serum with (0.1% sodium azide) and cured at 37°C for about 2 weeks. At the end of the 2 week cure, the samples were rinsed with deionized water, frozen in liquid nitrogen, then lyophilized overnight. Sample aliquots were analyzed by Fourier transform infrared spectroscopic analysis (FTIR) using pressed KBr pellets and by carbon coulometry using acidification for total inorganic carbon analysis and by combustion for total carbon analysis. The samples were further assayed for carbonate content in duplicate. The results of these assays are presented in Table 1 which shows that the subject compositions reacted to form carbonated hydroxyapatite having a dahllite crystal structure as confirmed by the weight percentage of carbonate contained in the resulting apatites.

Table 1.

Formulation	Mineralogy	% Carbonate
A 11.54 g C ₄ P(c), 1.4 g CC, 2.06 g oPA, 7.5 g 0.1 M SP	98% Dahllite	4.53
B 11.54 g C ₄ P(f), 1.4 g CC, 2.06 g oPA, 7.5 g 0.1 M SP	98% Dahllite	4.83

Abbreviations:

- C₄P = Tetracalcium phosphate, fine (f) 3 microns, course (c) 10 microns.
- CC = Calcium carbonate.
- oPA = Ortho-phosphoric acid.
- SP = Sodium phosphate, dibasic, 7-hydrate.
-

Example 2

A number of dry formulations were prepared having the compositions as set forth in Table 2.

Table 2.

Ingredient	1	2	3
Tetracalcium phosphate	45.0	43.95	13.73
Calcium oxides	0.17	0.33	0.56
Calcium carbonate	5.85	11.4	4.0
$\text{Ca}(\text{H}_2\text{PO}_4)_2 \cdot \text{H}_2\text{O}$	15.5		
Orthophosphoric acid		11.76	4.41
Na_2SiF_6	0.29	0.25	0.09

Each of the above formulations were ball milled in an alumina/silica mill jar with 0.5" x 0.5" alumina cylinders, where the container was from 25 to 50 volume percent full. The milling usually was contained for about 16 hours. In many cases, some caking was observed, particularly at the top of the container. The gasket at the top of the container to enclose the cover was cut, so as to allow for the release of gas. The mixing was at about 50 rpm.

After completion of the milling, the composition was combined with water, generally using about 0.35 parts of water to 1 part of solids. For preparing samples, 5 g of the solid mixture was combined with 1.75 g of deionized water and the mixture kneaded for about 5 min. The composition was introduced into a mold, allowed to set, and the sample removed for compressive strength testing. In some instances, the samples could not be easily removed from the mold, which could have affected the observed compression properties. The following table indicates the results, where the results are reported as the average of

- 18 -

from 3 to 4 determinations on different samples from the same composition.

5

Table 3.

	Ex.	Weight (g)	Load (lbs.)	Compressive Strength (psi)
10	1	0.72	367.9	8389

Considerable variation was noticed in the results. In example 1, the variation was from 5620 to 11794. Thus, while samples can be obtained having compressive strengths in substantial excess of 10,000 psi, the reasons why other samples from the same composition do not provide the same properties is believed to be related to defects in the specimen related to sample preparation. However, in any sample, products having properties in substantial excess of 10,000 psi compressive strength are achievable.

It is evident from the above results that the subject composition and the products derived therefrom provide a unique alternative to standard hydroxyapatite materials. Unlike standard hydroxyapatite compositions, the subject dahllite compositions can be constructed to contain carbonate at levels near or exceeding those normally occurring in natural bone. Since carbonate is intimately involved in the processes by which normal bone-resident cells are able to infiltrate, resorb and replace natural bone, the subject compositions provide products that better mimic natural calcified tissues in both form and function.

All publications and patent applications mentioned in this specification are indicative of the level of skill in the art to which this invention pertains. All publications and patent applications are herein incorporated by reference to the same extent as if each individual publication or patent application was

- 19 -

specifically and individually indicated to be incorporated by reference.

Although the foregoing invention has been described in some detail by way of illustration and example for
5 purposes of clarity of understanding, it will be obvious that certain changes and modifications may be practiced within the scope of the appended claims.

- 20 -

WHAT IS CLAIMED IS:

1. A biologically resorbable composition comprised of a substantially pure carbonate-substituted hydroxyapatite (Dahllite), having from about 2 to 10% by weight carbonate, and having a calcium/phosphate ratio in the range of about 1.33-2.0 and substantially free of blood and bone marrow, wherein the X-ray diffraction and Fourier transformed infra-red spectra of said composition differs from sintered and hydrothermally prepared hydroxyapatite.
2. A composition of Claim 1, wherein carbonate is present in an amount between about 2.5% and about 7% by weight and having a calcium/phosphate ratio of more than 1.5.
3. A composition according to Claim 1, wherein at least a portion of the hydroxyl groups of said hydroxyapatite are replaced with fluorine.
4. A composition according to Claim 1, prepared by the method comprising:
mechanically mixing under reaction causing conditions as reactants, at least one calcium source, an acidic phosphate source free of uncombined water, and a carbonate source, with an aqueous lubricant, wherein the lubricant is present in from about 15 to 50 weight per cent of the total composition to form a flowable mass; and annealing said flowable mass.
5. A composition according to Claim 4, wherein at least one of a biocompatible protein, polysaccharide or other biocompatible polymer, pharmacologically active agent or crystalline nuclei is included with said reactants or lubricant.

- 21 -

6. A composition according to Claim 5, wherein said composition comprises a biocompatible polymer which is collagen or chitin.

5 7. A composition according to Claim 4, wherein a sodium phosphate, carbonate or hydroxide is included in said lubricant.

8. A biologically resorbable composition comprised
10 of a substantially pure carbonate-substituted hydroxyapatite (Dahllite), having from about 2 to 10% by weight carbonate, and having a calcium/phosphate ratio in the range of about 1.33-2.0 and substantially free of blood and bone marrow, wherein the X-ray diffraction and
15 Fourier transformed infra-red spectra of said composition differs from sintered and hydrothermally prepared hydroxyapatite, prepared from a composition comprising:

from about 50 to 90 weight % of tricalcium phosphate;
20 from about 1 to 40 wt.% of calcium carbonate and from about 0 to 40 weight % of calcium hydroxide of the dry weight of the total reaction mixture.

9. A biologically resorbable composition according
25 to Claim 8, wherein said tricalcium phosphate is present in from about 75 to 90 weight %, said calcium carbonate is present in from about 2 to 18 weight % and said calcium hydroxide is present in from about 2 to 20 weight %.

30 10. A biologically resorbable composition according to Claim 8, wherein an acid phosphate source is present in from about 5 to 25 weight % of the dry weight of the total reaction mixture.

35 11. A formed object of the composition of Claim 1.

12. A formed object of the composition of Claim 4.

INTERNATIONAL SEARCH REPORT

 International application No.
 PCT/US93/09086

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : A01N 59/26; C01B 25/10, 25/16, 25/32; A61F 2/28

US CL : 424/602; 423/301, 305; 623/16, 901

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/602; 423/301, 305; 623/16, 901

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 5,009,898 (Sakuma et al.) 23 April 1991, see claim 1 and columns 3-4.	1-12
Y	US, A, 5,053,212 (Constantz et al.) 01 October 1991, see claims 10-18.	1-12
Y	US, A, 4,880,610 (Constantz et al.) 14 November 1989, see claims 7-12.	1-12
Y	US, A, 5,047,031 (Constantz) 10 September 1991, see claims 7-14.	1-12
Y	US, A, 5,129,905 (Constantz) 14 July 1992, see claims 8-16.	1-12

☐ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:	T	Inter document published after the international filing date or priority date and not in conflict with the application but cited to understand the principles or theory underlying the invention
A document defining the general state of the art which is not considered to be part of particular relevance	X	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	Y	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	A*	document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

03 JANUARY 1994

Date of mailing of the international search report

17 FEB 1994

 Name and mailing address of the ISA/US
 Commissioner of Patents and Trademarks
 Box PCT
 Washington, D.C. 20231

Facsimile No. NOT APPLICABLE

Authorized officer

JOHN PAK JD

Telephone No. (703) 308-1235

INTERNATIONAL SEARCH REPORT

I national application No.
PCT/US93/09086

BOX II. OBSERVATIONS WHERE UNITY OF INVENTION WAS LACKING

This ISA found multiple inventions as follows:

- I. Claims 1-10, drawn to a composition of carbonate-substituted forms of hydroxyapatite, classified in Class 424, subclass 602.
- II. Claims 11-12, drawn to a "formed object" of carbonate-substituted forms of hydroxyapatite, classified in numerous places depending on the nature of the formed object, including Class 623, subclasses 16 and 901.

The above two inventions lack unity with one another, because each of the invention group is directed to a different category of invention, wherein Group I is drawn to a chemical composition and Group II is drawn to an article of manufacture specially formed for its end use. Therefore, the two inventions are of separate inventive concept, and the search for one invention would necessitate searching in places where no pertinent art to the other invention may exist. Accordingly, the claims are not so linked as to form a single general inventive concept, and the claims thus lack unity of invention under PCT Rule 13 and 37 CFR 1.475.